

Record of Test

Project No: 0170038

Date: 21/08/2001

Project: BSI ROADMARKING TRIALS

Record Number: RT 28430

Page No: 1

PRODUCT SUBMITTED FOR PERFORMANCE TESTING AGAINST BS EN 1436 : 1998

Company : LKF Vejmarkering A/S
Type and Identification of Product : Premark Flex 10600
Colour : White
Location of Test Site : A11(T) Six Mile Bottom
Date of Test : 06.06.01
Roll-over Class : P5
% HGV : 12-25
Duration of Test : 12 months

Property : Line Number 42

Test	Average	Class
Luminance, β	32.62	B2
Colour (x)	0.3273	White
Colour (y)	0.3348	
Retroreflectivity Dry ($\text{mcd/m}^2/\text{lx}$)	100	R2
Retroreflectivity Wet ($\text{mcd/m}^2/\text{lx}$)	26	RW1
Skid Resistance	55	S3
Qd ($\text{mcd/m}^2/\text{lx}$)	142	Q3

Notes: Skid resistance corrected to 20 °C
Retroreflectivity measured using LTL2000 with 30m geometry

45 / 80

The results contained in this Record relate only to the items described



Reg No. FS 11403